Paint System Specifications

Primary Paint Systems at A Glance

AEP Span offers a range of high-performance paint systems engineered to meet architectural, environmental, and long-term durability needs. This cheat sheet provides a snapshot of primary paint systems, including coating types, film builds, gloss ranges, and warranty terms, helping you to select the right finish for your application and exposure conditions.

PAINT SUPPLIER NAME	# OF COATS	PAINT NAME	PRIMER	COLOR COAT	CLEAR	GLOSS	PAINT TYPE
Duranar® ULTRA-Cool®	2 Coats	Dura Tech® *5000*	0.15-0.30	0.70-0.80	None	8-15[1] at 60°	PVDF
Duranar® SUNSTORM® Mica-Effect	2 Coats	Dura Tech® *mx* (Pearlescent Mica)	0.15-0.30	0.70-0.80	None	15-30[3] at 60°	PVDF
Duranar® XL[7]	3 Coats	Dura Tech® *5000/mx* with Clear Coat	0.15-0.30	0.70-0.80	0.45-0.55	10-15[2] at 60°	PVDF
Duranar® Plus	2 Coats	Duranar® Plus Marine	0.70-0.80	0.70-0.80	None	8-15[1] at 60°	PVDF
Duranar® XL Plus	3 Coats	Duranar® XL Plus Marine	0.70-0.80	0.70-0.80	0.45-0.55	10-15[2] at 60°	PVDF
Duranar® ULTRA-Cool® Print	3-4 Coats	Dura Tech® *5000P* Print	0.15-0.30	0.70-0.80	1 or 2 color print layers	Various	PVDF
Coraflon® GR	3 Coats	Dura Tech® *5000/mx* with Graffiti-Resistant	0.15-0.30	0.70-0.80	0.45-0.55	10-35[4] at 60°	PVDF
Vintage®	1 Coat	Vintage®	NA	0.55-0.65	NA	10-20 at 60°	FEVE
Durastar® ULTRA-COOL®	2 Coats	Dura Tech™ *nt*	0.15-0.30	0.70-0.80	NA	25-35 at 60°	SMP
Beckry® Tex	2 Coats	Dura Tech® Rawhide	0.20-0.30	0.85-0.95	NA	2-5 at 60	Super Durable Polyester
Steelscape Prints® Rawhide	3 Coats	Dura Tech® Textured Print	0.20-0.30	0.85-0.95	1 color print layer	1-3 at 60	Super Durable Polyester
Durastar® ULTRA-Cool® Print	3-4 coats	Dura Tech® *xlp* Print	0.15-0.30	0.70-0.80	1 or 2 color print layers	Various	SMP

AEP SPAN PAINT NAME	WARRANTY DETAILS	PAINT WARRANTY YEARS (Film/Chalk/Fade)	ZINCALUME® CORROSION WARRANTY YEARS[5]
Dura Tech® *5000/mx*	Standard locations, greater than 1,000 ft from salt-water	40/40/40	25
Dura Tech® *5000/mx*	Less than 1,000 ft from salt-water	20/20/20	20
Duranar® Plus Marine	Less than 1,000 ft from salt-water, high build primer required	25/25/25	20
Duranar® *XL* Plus Marine	Less than 1,000 ft from salt-water, high build primer and clear	30/30/30	20
Dura Tech® *5000/mx* Puget Sound	Standard locations, greater than 1,000 ft from salt-water	40/40/40	25
Duranar® Plus Marine Puget Sound	Less than 1,000 ft from salt-water, high build primer required	30/30/30	20
Duranar® Plus Puget Sound	Less than 1,000 ft from salt-water, high build primer and clear	35/35/35	20
Dura Tech® *5000P* Print[6]	Standard locations, greater than 1,000 ft from salt-water	30/30/NA	25
Dura Tech® *5000/mx* with Graffiti-Resistant	Standard locations, greater than 1,000 ft from salt-water	40/40/40	25
Vintage®	Standard locations, greater than 1 mile from salt-water	20/20/NA	NA
ZINCALUME® Plus	Greater than 1 mile from salt-water	NA	25
Dura Tech® *nt*	Standard locations, greater than 1,000 ft from salt-water	25/25/25	25
Dura Tech® Rawhide	Standard locations, greater than 3,000 ft from salt-water	40/30/30	25
Dura Tech® Textured Print	Standard locations, greater than 3,000 ft from salt-water	30/30/NA	25
Dura Tech® *xlp* Print	Standard locations, greater than 1,320 ft from salt-water	25/25/NA	25

Print Notes:

1. Matte Black gloss 20-25.
2. Final gloss dependent on color coat selection.
3. ZACtique® II gloss: 15-25, Metallic Silver and Metallic Champagne gloss: 15-25, Metallic Copper/Copper Penny gloss: 20-30.
4. Dependent on color coat and clear coat gloss.
5. Submit warranty exception for locations less than 1 mile from salt water or for durations longer than 25 years in standard locations.
6. Marine options available dependent on specific print pattern.
7. Warranty duration dependent on variety of factors.

Customer Service Center
Tacoma, WA
Phone: 800-733-4955
Fax: 253-272-0791

For most current versions of literature please visit
www.aepspan.com

All information stated in the product sheet is correct at time of printing and subject to change without notice, check our website for the latest version. Duranar®, Durastar®, and Coraflon® are registered trademarks of PPG Industries, Inc. Vintage® is a registered trademark of Steelscape, LLC. ZINCALUME® is registered trademark of BlueScope Steel Ltd. ©2026 ASC Profiles LLC. All rights reserved. 0326 Printed in USA web